



Mykroy-Mycalex Ceramics

Glass-Mica Composites (Completely Inorganic)

MACHINABLE GRADES TECHNICAL DATASHEET

General Properties	UNIT	MM 400	MM 500	MM 1100	MM 1600
Density	g/cm ³	2.5	2.7	2.8	2.74
Moisture Absorption	%	Nil	Nil	Nil	Nil
Color	---	D-Gray*	L-Gray*	Cream	Off White
Mica Filler	---	Natural	Synthetic	Synthetic	Synthetic
Flammability	DOES NOT BURN				
Thermal Properties					
Max. Continuous Use Temperature	°F	750	930	1100	1560
	°C	400	500	600	850
Thermal Conductivity	W/m.K	.87	1.15	1.32	1.02
Coefficient of Thermal Expansion (x10 ⁻⁶)	/°C @ 25°C	12.5	11.57	10.48	9
	@ 350°C	11.0	10.53	9.74	10.46
	@ 500°C	---	---	9.39	10.69
	@ 750°C	---	---	---	15.81
Specific Heat	cal/g/°C	0.12	0.12	0.11	0.209
Electrical Properties					
Dielectric Strength	V/mil	730	530	420	480
	kV/mm	28.7	20.9	16.5	18.9
Arc Resistance	Seconds	245	260	345	300
Dissipation factor	1 MHz	0.0018	0.0013	0.0017	.003
Loss Index	1 MHz	0.012	0.009	0.012	.0207
Surface Resistivity	Ω/sq (25°C)	10 ⁹	10 ¹²	10 ¹¹	5 x 10 ¹³
Volume Resistivity	Ω-cm (25°C)	10 ¹⁰	10 ¹⁴	10 ¹²	2.6 x 10 ¹⁵
Dielectric Constant	1 MHz	6.7	6.9	6.8	6.91
Mechanical Properties					
Tensile Strength	psi	6000	6000	5000	6000
	MPa	41.4	41.4	34.5	41.4
Flexural Strength	psi	13,000	12,500	11,000	13,500
	MPa	89.6	86.2	75.9	93.1
Compressive Strength	psi	45,000	40,000	32,000	40,000
	MPa	310	276	221	276
Modulus of Elasticity	psi x10 ⁶	11.0	12.0	10.6	11.5
	GPa	75	82.7	73.1	79.3
Hardness - Rockwell	H	90	90	91	90
	A	46	46	47	47
Impact Strength— IZOD (notched)	Ft-lbs/in	1.8	1.7	1.3	1.8
	J/cm	0.961	0.908	0.694	0.961

Glass Bonded Mica Summary Specification – ASTM D 1039

* : D = Dark; L = Light

“To the best of our knowledge the information contained herein is accurate; however, Crystex Composites LLC does not accept any liability regarding the accuracy or completeness of such information. Further, such information is established using standard base material and thus may change if the product ordered by purchaser requires further processing of base material by us and/or the purchase. Purchaser has the sole responsibility in determining the suitability of any material described herein for the use contemplated and the processing of such material by purchaser.”